



Add: PV Oil Building, 148 Hoang Quoc Viet, Nghia Tan Ward, Cau Giay Dist, Hanoi

Phone: +84914132017/+84916652017/+84919712017

Website: anthanhbicsol.com **Email:** sales@anthanhbicsol.com

Product: PPT3034

Applications: Homo – PP for Injection Molding, Packaging, Fibers & Fabrics, so on.

Specifications:

Physical properties	Test Method	Unit	T3034
Density	ASTM D1505	g/cm ³	0.91
Isotactic Index	MPC PP-F-107	%	98
Melt Index (MI)	ASTM D1238	g/10 min	3.4
Mechanical			
Tensile Strength (Yield)	ASTM D638	MPa	38
Flexural Modulus - 1%	ASTM D790	MPa	1550
Impact Strength Notched Izod Impact			
23 oC	ASTM D257	J/m	5
Spiral Flow Length	MPC PP-A-301	cm	55
Hardness (Rockwell)	ASTM D785	RScale	95
Thermal			
Deflection Temperature under Load 0,45Mpa	ASTM D1525	oC	110
Softening poit (Vicat)	ASTM D648	oC	155