## NAN YA PLASTICS CORPORATION TAIRILIN Bottle Grade PET Resin

**Type No: 3802** 

Tairilin 3802 is a copolymer resin with a nominal intrinsic viscosity of 0.80dl/g. This resin posseses excellent melting characteristic, optimized crystallization rate, large process window and stability during injection / stretch-blow molding. Specifically, 3802 resin has the advantage of wide processing window during injection and stretch blow molding, this provides the lower generation of acetaldehyde and higher clarity in bottles. 3802 resin is suitable for applications of bottled water, cooking oil, soy sauce and alcoholic beverage applications or for the larger wide mouth bottles.

Tairilin 3802 resin is produced in a state of the art continuous polymerization technology and is combined with a strict quality monotoring system. The production facilities producing 3802 resin are approved by ISO9001 and ISO14001 and OHSAS 18001 systems. 3802 resin has been accepted by food and beverage companies as its outstanding quality for many years.

3802 resin conforms to FDA Regulation 177.1630 and European Directives, and is widely used for food and beverage packaging. 3802 resin is an environmental friendly product with the important advantage of being totally recyclable.

## **Technical Data Sheet**

Items			Units	Value		Test Method	
Intrinsic Viscosity			dl/g	0.800 ± 0.02		Refer to ASTM D4603	
Melting temperature			$^{\circ}$	242 ± 3		ASTM D3418	
Ash Content			%	≦ 0.02		Nan Ya Method	
Moisture			%	≦ 0.30		Nan Ya Method	
Acetaldehyde			ppm	≦ 1.0		Gas Chromatography	
Carboxylic end group			10 <sup>-6</sup> equ/g	30 ± 10		Titration Method	
Bulk Density			g/cm <sup>3</sup>	0.89 ± 0.05		JIS K-5101	
Chip Size		chips/2g	130 ± 3		Weight scale		
Fines		ppm	< 100		Nan Ya Method		
Color	L Value		-	86.5 ± 2.0		ASTM E1164	
	b Value		-	-1.8 ± 1.0		ASTM E1164	
The following are provided as suggesting value for reference							
Dew		point	${\mathbb C}$		-40		
Drying		Air flow		ft³/min	1/	per pound chip per hour	
Condition		Residence		hr	7~5		
		Temperature		${\mathbb C}$		160 ~ 170	
Moulding temperature				${\mathbb C}$	275 ~ 290		
Resin storage conditions				Store PET bag in dry and clean warehouse.			
at converter				Consume PET resin within 1 year from packed			
				date.			